

STICKY BACK FELT

Specifications

Part No.	Dimesions	Package Qty.	Comments
#160	3/16" X 2" X 25' with adhesive	24 per case	Most Common
#161	3/16" X 5/8" X 25' with adhesive	72 per case	
#162	3/16" X 3/4" X 25' with adhesive	64 per case	
#163	3/16" X 1" X 25' with adhesive	48 per case	
#164	3/16" X 1 1/2" X 25' with adhesive	32 per case	
#170	1/4" X 2" X 25' with adhesive	24 per case	Most Common
#171	1/4" X 5/8" X 25' with adhesive	72 per case	
#172	1/4" X 3/4" X 25' with adhesive	64 per case	
#173	1/4" X 1" X 25' with adhesive	48 per case	
#174	1/4" X 1 1/2" X 25' with adhesive	32 per case	
#180	1/8" X 2" X 50' with adhesive	24 per case	Most Common
#181	1/8" X 5/8" X 50' with adhesive	72 per case	
#182	1/8" X 3/4" X 50' with adhesive	64 per case	
#183	1/8" X 1" X 50' with adhesive	48 per case	
#184	1/8" X 1 1/2" X 50' with adhesive	32 per case	

NON-STICKY BACK FELT

Specifications

Part No.	Dimesions	Package Qty.	Comments
#165	3/16" X 2" X 25' without adhesive	24 per case	
#175	1/4" X 2" X 25' without adhesive	24 per case	

METAL BACK FELT

Specifications

Part No.	Dimesions	Package Qty.	Comments
#160M	3/16" X 2" X 25' with metal	24 per case	
#170M	1/4" X 2" X 25' with metal	24 per case	

STICKY BACK FELT PRODUCT DATA CHART

S.A.E. Felt Specifications #F-15

PROPERTIES

High Needle Density, Self Supported

	Grey	Grey	Grey
Color	Grey	Grey	Grey
Thickness/Nominal	1/8"	3/16"	1/4"
Thickness/Limits In.	.105-.1450	.1670-.2070	.230-.270
Weight/oz. per Sq. yard	15-19	23-27	32-36
Density 1% specific gravity	15.4	15.4	15.4
Actual Wool content	55%	55%	55%
Carbontet/Soluble Max.	8%	8%	8%
Walter Soluble Max.	6%	6%	6%
Combined Carbontet/Water Soluble	14%	14%	14%
Ash Max.	5%	5%	5%
Tensile Strength Min.	not measurable	not measurable	not measurable
Splitting resistence Min.	not measurable	not measurable	not measurable